

Technical Data Sheet

Material description



is a high temperature insulation board or shape part, made out of exfoliating vermiculite and an inorganic binder. The material is free of asbestos fibers and organic substance.

Specification

Type		Grenamat AS
Designation		Vermiculite board / shaped part
Dimension of board	mm	1220 x 2440 x th.8-35; 800 x 600 x th.15-80
Tolerance of thickness	mm	± 0,2
Tolerance of format	mm	± 5
Classification temperature	°C	1150
Building class material according to DIN 4102		A1, non-combustible
Building class material according to EN 13 501:1		A1, non-combustible
Bulk density	kg/m ³	400 – 750; parameters below for 500 kg/m ³
Cold compressive strength at deformation of 10%	N/mm ²	4,38
Linear shrinkage after 12 h at 1150 °C	%	1,4
Specific heat capacity	kJ/kgK	0,8
Thermal conductivity		
200 °C		0,211
400 °C	W/mK	0,224
600 °C		0,254
800 °C		0,296
1 000 °C		0,303
Thermal length change	m/mK	8,5 · 10 ⁻⁶
Moisture content (in foil)	%	2 - 3
Chemical analysis:		
Al ₂ O ₃		9,10
SiO ₂	%	54,75
MgO		23,48
Alkali		5,21

All technical data are mean values from the production, which are subject to the usual fluctuations. They shall not be deemed as a guarantee of certain properties in the sense of a warranty. All data correspond to the latest state of the art and have been presented and described to the best of our knowledge. Modifications resulting from the latest recognitions are possible. Errors and omissions are not excluded. Our terms of delivery and payment are valid in the event of any possible liability. Ask for the safety data sheet. This publication renders all previous ones invalid.

Řezníček Petr
Project manager

20.2.2007



Čs. armády 540, 391 81 Veselí nad Lužnicí, CZ
tel.: +420/381 549 111 fax: +420/381 581 071
e-mail: grenamat@grenamat.cz www.grenamat.cz
IČO: 46678832 DIČ: CZ46678832
Zápis v OR u KS v Českých Budějovicích oddíl B, vložka 484.

